

750

HOT-MELT ADHESIVE FOR AUTOMATIC EDGE BANDING MACHINES STRAIGHT EDGE BANDING

Description

For bonding melamine edgings, treated PVC and ABS, impregnated paper, polyester and wood edgings to wood based substrates like MDF, solid wood or chipboard.

750 IS CHARACTERIZED BY:

High adhesion to a wide range of materials
Long open time
Medium viscosity

Above characteristics make the adhesive especially suitable for

Bonding on the same production line of edgings of different nature;
Use on working lines operating at a speed from 15 m/min up to 30 m/min.

CHARACTERISTICS

Composition	: EVA copolymers, synthetic resins, inert fillers
Shape	: granules
Colours	: natural, nut, white

TECHNICAL DATA

Softening point (Ring & Ball)	: 102 - 107°C.
Brookfield Viscosity at 210°C	: 85000 - 95000 mPa.s

The values in this table must not to be considered as specifications

APPLICATION

Recommended machine speed: at least 15 m/min. A high machine speed enhances the bonding performances.

Application temperature: 200-210°C on to the roller spreader; temperature into the melting tank should be such as to ensure the correct temperature on to the roller when the working line is running. This condition is usually reached at a temperature in the range 160°-180°C, depending on the type of melting tank.

750 is characterized by an excellent melt stability. During work breaks, anyhow, it is recommended to reduce temperature in the melting tank and on to the roller under 160°C, to prevent thermo-oxidative degradation and the need of having recourse too often to cleaning of spreader unit.

In order to reduce risk of charring it is recommended to keep high the level of melt in the tank; this also keeps temperature of the melt from any abrupt change when feeding the tank with additional cold hot-melt granules.

Surface preparation and conditioning of materials: all surfaces of edgings should be clean and dry, free from dust or any contaminants resulting from sanding. If materials to be bonded are stored for some time at low temperature, they should be adequately conditioned in a heated and dry room prior to use.

Coverage: the quantity of hot-melt adhesive to use in order to obtain a good bond is generally in the range 180 and 250 g/m², depending on the nature of edging and substrate.

A larger amount is usually required for thick edgings and chipboard lacking compactness.

A smaller quantity can prove enough in case of thin edgings to apply to solid wood.

Pressure of rollers: in order to get the best bond results, the thicker and harder the edging used, the higher should be the force applied by pressure rollers.

STORAGE STABILITY

Can be stored for 18 months in closed (unopened) packaging in a dry place

All recommendations relating to the application and use of Fratelli Zucchini products have been given in good faith, based on the company's knowledge and experience. Products must be appropriately stored, handled and applied in normal conditions, as indicated on their respective Technical Datasheet. The variability of materials, substrates and conditions of use is such that no warranty of their functionality for a specific application can be deducted from this information, written recommendation or any other type of suggestion offered. Each user has the responsibility to make adequate evaluations on the efficacy of Fratelli Zucchini materials, products, services, recommendations and suggestions for the specific application required and must accomplish sufficient testing to ascertain that the final product will be safe and sound for the final purpose of the end-user. Fratelli Zucchini cannot be considered liable for any damage, direct or indirect derived from an incorrect use of the products